

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-012387

(43)Date of publication of application : 16.01.1996

(51)Int.Cl.

C04B 7/153

C04B 11/28

(21)Application number : 06-149413

(71)Applicant : MASUDA YOSHITAKA

MASUDA YOSHIHIRO

MIURA IWAO

(22)Date of filing : 30.06.1994

(72)Inventor : MASUDA YOSHITAKA

(54) HIGH SULFATE SLAG CEMENT AND ITS PRODUCTION**(57)Abstract:**

PURPOSE: To inexpensively produce a high sulfate slag cement excellent in quick setting, hardening and high-early-strength, capable of suppressing neutralization rate and obtaining a stable hardened body.

CONSTITUTION: This high sulfate slag cement is obtained by adding a stimulating agent, which uses blast furnace slag, coal ash, gypsum, lime stone, dolomite and fluorite as raw materials and is composed of a clinker containing 12.0-21.0% SiO₂, 7.0-26.0% Al₂O₃, 0.2-7.3% Fe₂O₃, 50.0-67.0% CaO, 5.5-18.0% MgO, 4.0-18.0% SO₃, 0.03-0.38% Na₂O, 0.24-0.35% K₂O, 0.10-0.43% MnO, 0.6-2.8% f-CaO and 0.7-1.5% F as essential structural components, gypsum anhydrate and aluminum sulfate or sodium citrate into a cement basis of blast furnace slag decreased in alumina and calcium and increased in magnesia and mixing and finely pulverizing the resultant mixture.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]